



THERMALLY CONDUCTIVE PRINTED CIRCUIT BOARD SUBSTRATE.

Tlam SS 1KA is a thermally conductive PCB Substrate. The substrate consists of a copper circuit layer bonded to an aluminum or copper base plate with Laird Technologies' 3 watt/m-K 1KA dielectric. Tlam SS 1KA materials are processed through standard FR4 print and etch operations.

Tlam SS 1KA has 8-10 times better thermal conductivity compared to FR4 and this is the key to keeping components cool. The Tlam SS 1KA boards run through standard pick and place SMT and manual wire bond processes.

Tlam SS 1KA is designed for applications that require the best thermal performance and resistance to thermal cycling. Customers have found that Tlam SS 1KA reduces the stress on solder bonds with ceramic devices.

Standard constructions are made with 1 and 2 ounce copper and 0.040 (1 mm) and 0.062 (1.6 mm) inch thick aluminum. Custom constructions of heavier weight circuit copper and thicker aluminum and copper base plates are also available.

FEATURES AND BENEFITS

- UL® 746 B Electrical/Mechanical RTI as high as 130°C
- RoHS compliant
- Environmentally green
- Lead free solder compatible
- Compliant for low bond stress

APPLICATIONS

- Network DC/DC power converters
- Battery powered equipment DC/DC power converters
- Ultra bright LED substrate

global solutions: local support.™

Americas: +1.800.843.4556

Europe: +49.8031.2460.0

Asia: +86.755.2714.1166

CLV-customerservice@lairdtech.com

www.lairdtech.com/thermal

Tlam™ SS 1KA

Thermally Conductive PCB Substrate

OPERATING VOLTAGE	UNITS	Tlam SS 1KA04	Tlam SS 1KA06	Tlam SS 1KA08
Continuous AC	VAC	50	120	240
Continuous DC	VDC	95	225	450
Peak Recurring	Vp	140	300	600
THERMAL PROPERTIES	UNITS	Tlam SS 1KA04	Tlam SS 1KA06	Tlam SS 1KA08
Thermal Conductivity*	Watt/m °K	3	3	3
Thermal Resistance	°C-in ² /watt (°C-cm ² /watt)	0.05 (0.34)	0.08 (0.52)	0.11 (0.70)
Glass Transition Temperature	°C	105	105	105
Operating Temperature, Maximum	°C	110	120	130
Soldering Temperature, Maximum	°C	288	288	288
Heat Capacity	J/g °K	1.53	1.53	1.53
ELECTRICAL PROPERTIES	UNITS	Tlam SS 1KA04	Tlam SS 1KA06	Tlam SS 1KA08
Dielectric Constant @ 1KHz/1MHz		4.3/4.1	4.3/4.1	4.3/4.1
Dissipation Factor @ 1KHz/1MHz		0.008/0.035	0.008/0.035	0.008/0.035
Capacitance @ 1KHz/1MHz	pF/in ²	244/230	161/153	121/115
Volume Resistivity	ohm-cm	1.20E+14	1.20E+14	1.20E+14
Surface Resistivity	ohm	1.00E+10	1.00E+10	1.00E+10
Dielectric Strength	V/mil (kV/mm)	650 (16.5)	800 (20.3)	800 (20.3)
Withstand Voltage	VDC	1800	2500	3500
MECHANICAL PROPERTIES	UNITS	Tlam SS 1KA04	Tlam SS 1KA06	Tlam SS 1KA08
Dielectric Thickness	inches (mm)	0.004 (0.102)	0.006 (0.152)	0.008 (0.203)
Peel Strength	lbs/in (Kg/cm)	4.5 (0.8)	4.5 (0.8)	5.0 (1.0)
CTE in XYZ axis < Tg	ppm	32/43	32/43	32/43
CTE in XYZ axis > Tg	ppm	81/171	81/171	81/171
Tensile Strength	MPa	52.2	52.2	52.2
Elongation 25/150°C	%	0.8/1.1	0.8/1.1	0.8/1.1
Young's Modulus @ 25/150°C	MPa	9700/2700	9700/2700	9700/2700
Poisson's Ratio @ 25/150°C		0.26/0.16	0.26/0.16	0.26/0.16
Flexural Strength	MPa	49.7	49.7	49.7
CHEMICAL PROPERTIES	UNITS	Tlam SS 1KA04	Tlam SS 1KA06	Tlam SS 1KA08
Water Absorption after 168 hours	% wt.	0.5	0.5	0.5
Out-Gassing-Total Mass Loss	% wt.	0.57	0.57	0.57
Collect Volatile Condensable Material	% wt.	0.06	0.06	0.06
AGENCY RATINGS & DURABILITY	UNITS	Tlam SS 1KA04	Tlam SS 1KA06	Tlam SS 1KA08
UL Continuous Operating Temperature	°C	110	120	130
UL Flammability	E165095	94V0	94V0	94V0
Comparative Tracking Index		600	600	600
Solder Float (3 min. @ 288°C)		Pass	Pass	Pass

*As measured on dielectric compound only.

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

THR-DS-Tlam-SS-1KA 0110

Any information furnished by Laird Technologies, Inc. and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird Technologies materials rests with the end user, since Laird Technologies and its agents cannot be aware of all potential uses. Laird Technologies makes no warranties as to the fitness, merchantability or suitability of any Laird Technologies materials or products for any specific or general uses. Laird Technologies shall not be liable for incidental or consequential damages of any kind. All Laird Technologies products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2010 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Technologies Logo, and other marks are trade marks or registered trade marks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird Technologies or any third party intellectual property rights. A16040-00 Rev D, 1/22/10.